



Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

FLEXmark® V 200 R WHITE OPAQUE NO PS

GENERAL DESCRIPTION:

This is a 2.4 mil (61 micron) rigid white opaque polyvinyl chloride (PVC - Vinyl) film.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES**		
Thickness mil (micron)	Film: 2.4 (61) +/- 10 %	DIN 53370
Dimensional Stability (%)	15 maximum	284°F (140°C) for 10 minutes
Tensile Strength (N/sq mm)	40 minimum	DIN EN ISO 527-1-3
60° Gloss	65 minimum	DIN 67530
Optical Density	3.1 minimum	

** For guidance only, not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs.

EXPECTED EXTERIOR LIFE	Two years vertical exposure, mid continental North America (for adhesive coated film)
SERVICE TEMPERATURE RANGE	-40°F to 176°F (-40°C to 80°C)
STORAGE STABILITY	Six month for free film stored at 70°F (21°C) and 50% RH Two years for adhesive coated film stored at 70°F (21°C) and 50% RH.

* FLEXmark is a registered trademark of FLEXcon Company, Inc.

07/03/2007

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.